


## Product Datasheet

### TMS1025

The copper braid is used as a super flexible conductor for all electric connection requirements, including power, earthing and equipotential connections.

It results from the use of a number of standard wires with diameter of 0.20 mm, twined together to form a cord.

More cords twined together can produce a small cross-sectioned braid or further secondary cords which, twined again, make it possible to get the desired cross-section.



#### Main

Family	Prefabricated earthing braids
Version	Flat tinned copper earthing braids
Code	TMS1025
Reference	TMS 10-300-8
Type	Flat
Number per package	10
Weight (kg)	0.033
Current (A)*	86
Sect. (mm <sup>2</sup> )	10
S (mm)	2.1 <sup>+0.5</sup> <sub>-0.5</sub>
L (mm)	300 <sup>+11</sup> <sub>-1</sub>
A (mm)	17 <sup>+0.5</sup> <sub>-0.5</sub>

B (mm)	$22^{+1}_{-1}$
C (mm)	$9^{+0.5}_{-0.5}$
D (mm)	$8.5^{+0.5}_{-0.5}$

\* Current calculated with a temperature rise  $\Delta T=35$  °C respect to a reference room temperature of 35 °C

### Technical Features

**Material:** tinned copper Cu-ETP 99.90% EN 13602

Standard wire  $\varnothing$  0.20 mm

**Resistivity:** 0.0172  $\Omega$  mm<sup>2</sup>/m

Compliant to EN 45545-2 for railway applications



### Flat type copper braids

Flat type made using the same process as in tubular braids but flattening it between rollers to the desired dimensions.

It is used for power, earthing and equipotential connections.

In power applications, it makes flexible connections which easily compensate offsets between elements to be interconnected, and provides excellent buffering of vibrations induced by, i.e., connection to a transformer.

With the same cross-section, it can take a higher current density than cables or copper bars.

Please contact Teknomega for non-specified tolerances.